



- De-waxes, etches, cleans, de-greases and prepares bare fiberglass for painting
- Easy to use formula
- Works on all fiberglass surfaces
- Biodegradable with no VOC content
- Part of an easy 1-2-3 system of bottom painting



Bio-Blue Hull Surface Prep 92 is a powerful blend of cleaning agents and silica grit that de-waxes, etches, cleans, and prepares bare fiberglass for painting. Regardless of the boat's age, the initial surface preparation is imperative. Residual parting agents utilized by the boat manufacturer to "pop" the boat from the mold may still be present, although not visibly apparent. This solvent-free product is designed to provide an easy and trouble-free method of removing unwanted contaminants, grease, wax, dirt, and mold release agents from fiberglass surfaces prior to painting. When used in conjunction with 6998 Skip Sand Primer or 4700/4701 Pettit Protect High Build Epoxy Primer and antifouling paint, it is part of an easy 1-2-3 system of bottom painting.

Directions for use:

Pour out some of the 92 Bio-Blue into a roller pan, then using a short nap roller (3/16 inch maximum) apply the 92 Bio-Blue Hull Surface Prep to an area approximately 5 feet by 5 feet. Once the area has been covered with the Bio-Blue, scrub the surface using a fine to medium Scotch-Brite pad. The scrubbing should be done by hand in a circular motion. Be sure to wear splash goggles and rubber gloves and do not let 92 Bio-Blue come in contact with your skin. Be sure that all areas coated with the 92 Bio-Blue have been scrubbed with the Scotch-Brite pad. Stay within the 5 feet by 5 feet area and do not attempt to scrub beyond this area once the 92 Bio-Blue has been rolled on. After the section has been scrubbed, wipe the area with a wet sponge until all of the 92 Bio-Blue and scrubbing residue has been completely removed from the surface. Rinse sponge and change rinse water often. Where feasible, hose off the surface residue and residual 92 Bio-Blue with fresh water. Continue prepping the hull in this manner until the entire surface to be painted has been thoroughly cleaned. The gel coat should have a frosty look when the surface has been properly prepared.

Easy 2-Step Method - Thoroughly clean and prep hull using 92 Bio-Blue and a Scotch-brite pad as described above. Make sure that the entire surface has a dull, frosty finish. Wipe surface to remove any excess moisture and apply two coats of any Hydrocoat Antifouling Paint.

PHYSICAL DATA	APPLICATION DATA	ASSOCIATED PRODUCTS
COLOR: Blue viscous liquid COVERAGE: Approximately 600 sq. ft/gal. VOC: 0 g/l max. (0 lbs/gal) FLASH POINT: None pH: 8.0-9.0	METHOD: Apply by using a short nap (3/16 inch maximum) roller followed with a Scotch-Brite pad. NUMBER OF APPLICATIONS: One DRY TIME PRIOR TO PAINTING: 1 hour min.	6149 EZ Prime 6998 Skip-Sand Primer 4700/4701 High Build Epoxy Primer Hydrocoat Antifouling Paints Pettit Antifouling Paints Pettit, Z*Spar, Shipendec Topside Paints



Pettit Technical Bulletin

Bottom Painting Bare Fiberglass

There are four methods used to apply antifouling paint to bare fiberglass hulls. One of the most important parts to each system is to be sure the bottom is completely cleaned and de-waxed prior to sanding or applying any products. All bare fiberglass, regardless of age, should be thoroughly cleaned with 92 Bio-Blue Hull Surface Prep or de-waxed several times with Pettit D-95 Dewaxer or 120 Brushing Thinner. When using 92 Bio-Blue Hull Surface Prep, pour out some of the 92 Bio-Blue into a roller pan, then using a short nap roller (3/16 inch maximum) apply the 92 Bio-Blue Hull Surface Prep to an area approximately 5 feet by 5 feet. Once the area has been covered with the Bio-Blue, scrub the surface by hand in a circular motion using a fine to medium Scotch-Brite pad. Wipe the area with a wet sponge until all of the 92 Bio-Blue and scrubbing residue has been completely removed from the surface. Rinse sponge and change rinse water often. Where feasible, hose off the surface residue and residual 92 Bio-Blue with fresh water and let dry. When using D-95 Dewaxer or 120 Brushing Thinner, apply in a circular motion, applying a liberal wet coat. Wipe dry with a clean rag to remove contaminants. Change applicator and cleaning rags often. Follow all directions on product label closely. Modern boat hulls constructed of Vinylester resins generally retain more mold release waxes, therefore, they should be cleaned and de-waxed at least four times prior to applying primer coat.

Application Methods:

I. Sanding Method

II. High Build Epoxy Primer Method

III. Sandless Method:

IV. Easy 2-Step Sandless Method

I. Sanding Method:

Thoroughly clean and de-wax the hull as described above with 92 Bio-Blue Hull Surface Prep, D-95 Dewaxer, or 120 Brushing Thinner. Sand thoroughly with 80 grit sandpaper to a dull, frosty finish and rewash the sanded surface with 120 Brushing Thinner to remove sanding residue. Careful observation of the above instructions will help ensure long term adhesion of this and subsequent years' antifouling paint. Apply at least two coats of antifouling paint.

II. High Build Epoxy Primer Method:

This method is highly recommended where blister protection is a concern or on boats that have recently been stripped by a blasting method. Pettit Protect High Build Epoxy Primer is a heavy duty, two component epoxy coating for use where maximum resistance to fresh or salt water is required. It reduces water absorption in fiberglass hulls, making it an excellent choice for the prevention and repair of osmotic blisters. Pettit Protect's high-solids formula allows for quicker and easier application with fewer coats necessary for effective protection.

Thoroughly clean and de-wax the hull as described above with 92 Bio-Blue Hull Surface Prep, D-95 Dewaxer, or 120 Brushing Thinner. Sand the surface thoroughly with 60 grit sandpaper and rewash with 120 Brushing Thinner to remove sanding residue. Apply at least three coats of Pettit Protect High Build Epoxy Primer following the application and recoat instructions. Total dry film thickness is more important than the actual number of coats applied. On metal and fiberglass, if 12 mils total DFT is not achieved with three coats, additional coats are recommended until 12 mils total DFT is achieved. Finish with two coats of Pettit antifouling paint. For detailed application instructions on Pettit's High Build Epoxy Primer see Technical Bulletin *TB1000 Gelcoat Blister Repair and Prevention*.



Pettit Technical Bulletin

Bottom Painting Bare Fiberglass

A single coat of Pettit Protect High Build Epoxy Primer can also be used in place of Pettit 6998 Skip-Sand Primer for the Sandless Method providing the hull has been thoroughly cleaned and prepped using 92 Bio-Blue and a Scotch-Brite pad.

III. Sandless Method:

To eliminate the sanding operation, thoroughly clean and de-wax the hull as described above with 92 Bio-Blue Hull Surface Prep, D-95 Dewaxer, or 120 Brushing Thinner. Then apply one thin coat of Pettit 6998 Skip-Sand Primer. Use a 3/16" or less nap when applying by roller, a 1/8" nap roller is recommended. These rollers can be found in mohair type (usually called "adhesive applicators") or solvent resistant foam type. Consult the primer label for complete application and antifouling top coating instructions. Let dry in accordance with the primer labels and apply bottom paint. Pettit 6998 Skip Sand Primer is a pre-treatment primer designed to adhere tenaciously to un-sanded and de-waxed fiberglass gelcoat. When properly top coated with antifouling paint, the primers and antifouling will bond together strongly, resulting in a finish with excellent overall adhesion. These primers are ideal for use over vinyl ester gelcoats, where sanding of the gelcoat may void osmotic blister warranties. Skip Sand Primer may be used over conventional gelcoats as well, and as a tie-coat between two-part epoxy primers and antifouling paints. Pettit 6998 Skip Sand Primer has a fairly large time window when antifouling paint must be applied. Antifouling paint can be applied in as little as a few hours or up to 7 days making it an ideal primer to use when the antifouling application is not rushed and can be performed over two or more days.

A single coat of Pettit Protect High Build Epoxy Primer can also be used in place of Pettit 6998 Skip-Sand Primer for the Sandless Method providing the hull has been thoroughly cleaned and prepped using 92 Bio-Blue and a Scotch-brite pad.

IV. Easy 2-Step Sandless Method

Thoroughly clean and prep hull using 92 Bio-Blue and a Scotch-brite pad as described above. Wipe surface to remove any excess moisture and apply one of the Hydrocoat antifouling paints.

Tips for Using Skip Sand Primer

Allow the 6998 Skip Sand Primer to dry completely tack-free. The primer has dried tack-free when no surface tackiness is felt when applying moderate pressure with a fingertip. Use the chart below to determine when to apply antifouling paint. Humidity, ventilation, film thickness, as well as temperature can all affect the rate at which this Primer dries.

6998 Skip Sand Primer Application Temperature	When Used Under All Ablative or Hard Bottom Paints <i>Must be Completed Within 7 Days</i>
50 - 60 Degrees	Apply bottom paint after a minimum 4 hours and up to a maximum of 7 days
70 Degrees	Apply bottom paint after a minimum 3 hours and up to a maximum of 7 days
80 - 100 Degrees	Apply bottom paint after a minimum 2 hours and up to a maximum of 7 days