

## Advance™ Monofilament

<b>LB. Test</b>	<b>Diameter (In.)</b>
4	0.008"
6	0.010"
8	0.011"
10	0.012"
12	0.014"
14	0.015"
17	0.016"
20	0.018"
25	0.020"

## Castable Invisiline™ 100% Fluorocarbon

<b>Test Lb.</b>	<b>Diameter (Inches)</b>
3	0.006
4	0.007
5	0.0075
6	0.008
7	0.0085
8	0.009
10	0.011
12	0.012
14	0.013
17	0.016
20	0.017

## Elite™

Test Lb.	Diameter (Inches)
4	0.008
6	0.010
8	0.011
10	0.012
12	0.014
14	0.008
17	0.016
20	0.018
25	0.020
30	0.022

## Performance Braid

Test (Lb. / Kg.)	Diameter (In. / Mm.)	Mono Lb. Test Equiv. Dia.
6 / 2.7	0.006 / 0.14	2
10 / 4.5	0.008 / 0.2	4
20 / 9.1	0.009 / 0.23	6
30 / 13.6	0.011 / 0.29	8
40 / 18.2	0.013 / 0.33	10
50 / 22.7	0.014 / 0.34	12
65 / 29.5	0.016 / 0.4	17
80 / 36.4	0.018 / 0.45	20
100 / 45.5	0.021 / 0.54	25
130 / 59.1	0.024 / 0.60	40

## ProMix™

Test Lb.	Diameter (Inches)
4	0.008
6	0.010
8	0.011
10	0.012
12	0.013
14	0.014
17	0.016
20	0.017

## 832 Advanced Superline®

Test (Lb. / Kg.)	Diameter (In. / Mm.)	Mono Lb. Test Equiv. Dia.
6 / 2.7	0.006 / 0.14	2
8 / 3.6	0.007 / 0.18	3
10 / 4.5	0.008 / 0.2	4
15 / 6.8	0.0085 / 0.22	5
20 / 9.1	0.009 / 0.23	6
30 / 13.6	0.011 / 0.29	8
40 / 18.2	0.013 / 0.33	10
50 / 22.7	0.014 / 0.34	12
65 / 29.5	0.016 / 0.4	17
80 / 36.12	0.018 / 0.45	20

## Siege™

Test Lb.	Diameter (Inches)
4	0.008
6	0.01
8	0.011
10	0.012
12	0.014
14	0.015
17	0.016
20	0.018
25	0.02
30	0.022

## Superior

Test Lb.	Diameter (Inches)
6	0.01
8	0.011
10	0.012
12	0.014
15	0.016
20	0.018
25	0.02
30	0.022
40	0.024
50	0.028
60	0.032
80	0.036
100	0.039
130	0.047
150	0.047
200	0.055
250	0.059
300	0.063
400	0.071
500	0.079
650	0.094